



Specification Sheet

BoneDry™ RP

2034-C Van Buren Ave. • Indian Trail, NC 28079 • Phone: 704.334.8222

BoneDry™ RP Waterproofing Membrane is a modified asphalt emulsion developed for use as a below grade waterproofing barrier. **BoneDry™ RP**'s low vapor permeance, outstanding adhesion, and superior combination of hardness and flexibility make it a great choice for any below grade waterproofing application. Some typical applications include waterproofing residential basements and crawl spaces.

BoneDry™ RP is spray applied and can instantly build virtually any thickness¹ your job demands. Instant thickness means you can install the remainder of your waterproofing system immediately after the product has been sprayed – no additional trips to complete waterproofing because your membrane isn't cure.

Property	Test Method	Value
Color		Black/Brown
Non Volatile Solids		63% ± 2%
Density		8.3 lbs/gal.
Coverage Rate		22-25 sq. ft./gal.
Thickness		40 mil (Dry)
Elongation	ASTM D-412	> 500%
Tensile Strength	ASTM D-412	22 psi
Adhesion to Concrete	ASTM C-836	Exceeds
Water Degradation	ASTM D-2939	No Degradation
Water Vapor Permeance	ASTM E-96 Wet	0.0267 gr/hr*sq.ft.
Mold Growth & Bacterial Attack	ASTM D-3273, 3274	No Degradation
Low Temp Flexibility	ASTM C-836	No Cracking
Crack Bridging	ASTM C-836	No Loss of Adhesion
Hardness	ASTM C-836	75

For more application
information visit
www.drydogbarriers.com
or email us
info@drydogbarriers.com

Applications

- Poured Foundations
- Retaining Walls
- Cavity Wall air barrier
- Seamless Flashing



BoneDry™ RP waterproofing membrane shown with available 12" DrainMax™ foundation strip drain to make the BD1000 Waterproofing System

¹ To obtain recommended thickness this product must be used with BoneDry™ Accelerator.

The information and recommendations discussed in this publication are believed to be correct. However, this should not be accepted as a guarantee of their accuracy, and confirming test should be run in your own plant or laboratory. No statement should be construed as a recommendation for any use, which would violate any patent rights. Nothing contained herein shall constitute a warranty with respect to the products described or their use.

BoneDry™ RP
Issue: A
Revision: 2
Date: 02/15/07