



Specification Sheet

BoneDry™ TG

2034-C Van Buren Ave. • Indian Trail, NC 28079 • Phone: 704.334.8222

BoneDry™ TG is a commercial grade trowelable waterproofing mastic based on polymer modified asphalt emulsion. **BoneDry™ TG** is used as a below-grade exterior waterproofing compound and exhibits excellent strength, adhesion, and flexibility. **BoneDry™ TG** is a premium grade waterproofing compound used in commercial building construction for detailed applications.

BoneDry™ TG can be effectively used as a sealant or patch for tie holes, protrusions, penetrations, cold joints and honeycombs. This product is also a great choice for repairing cracks, seam failures and other water penetration points on existing structures. **BoneDry™ TG** is also used as an adhesive for flashing and other termination materials.

Technical Data

Color		Black/Brown
Solids		63% ± 2%
Thickness		40-60 mil dry
Tensile Strength	ASTM D-412	87 psi
Elongation	ASTM D-412	1800%
MVT	ASTM E-96	0.19 gr/hr*sq.ft
Adhesion to Concrete	ASTM C-834	Exceeds
Shore Hardness	ASTM C-836	75
Crack Bridging	ASTM C-836	Exceeds
Low Temp Flexibility	ASTM C-836	No Cracking
Perm Rating	ASTM C-836	0.38 perms

For more application
information visit
www.drydogbarriers.com
or email us
info@drydogbarriers.com

Applications

- Masonry Foundations
- Poured Foundations
- Pre-Cast Foundations
- Horizontal Waterproofing
- Planters
- Retaining Walls
- Cavity Wall Air Barrier

The information and recommendations discussed in this publication are believed to be correct. However, this should not be accepted as a guarantee of their accuracy, and confirming test should be run in your own plant or laboratory. No statement should be construed as a recommendation for any use, which would violate any patent rights. Nothing contained herein shall constitute a warranty with respect to the products described or their use.

BoneDry™TG
Issue: A
Revision: 1
Date: 02/15/07